



TYPICAL PHYSICAL PROPERTIES

Property	Excellay
Thickness (mm)	7 ± 0.3
Nominal Density (Kg/m3)	120
Laminate (Topside)	Excellay Gold Laminate (Polyethylene) Polypropylene Mesh
Laminate (Downside)	None
Breaking Force (N/50mm)	50.1
Elongation (%)	13.25
Work of Compression (J/m2) (After Dynamic Loading)	128.45
Retention of W.O.C (After Dynamic Loading)	86.3%
Deflection @ 100kPa (After Dynamic Loading)	4.85
Loss of Thickness:	
a) Static Loading (after 24 hours)	N/A
b) Dynamic Loading (1000 cycles)	3.6%
AS 4288 – 2003 Classification	Luxury - L
Foam	Re-bonded Polyurethane Treated with Ultra-Fresh™

PACKAGING INFORMATION

	Length (m)	Width (m)	Area (m2)	Weight (kg)	Polywrap
Individual Rolls	10	1.80	18	15	Excellay Orange Wrap Printed Black Polyethylene

Excellay is a Registered trade name.

All statements and technical information contained herein are based on tests we believe to be reliable but the accuracy thereof is not guaranteed. Industry Purchasers assume all risk and liability resulting from the use of this product and must confirm the suitability thereof by their own test. Conditions of Sale contain a limited warranty against manufacturing defects.

Version No: 1.4	Effective Date: December 2008	Document No: DF8410
Location: DMS		Page 1 of 1
PRINTED COPY - UNCONTROLLED		