



## TYPICAL PHYSICAL PROPERTIES

Property	Ultralay
Thickness (mm)	5 ± 0.3
Nominal Density (Kg/m <sup>3</sup> )	170
Laminate (Topside)	Dunlop Carpet Cushion Kraft Paper
Laminate (Downside)	HD Blue Laminate
Breaking Force (N/50mm)	112
Elongation (%)	7%
Work of Compression (J/m <sup>2</sup> ) (After Dynamic Loading)	80.56
Retention of W.O.C (After Dynamic Loading)	96%
Deflection @ 100kPa (After Dynamic Loading)	2.5mm
Loss of Thickness:	
a) Static Loading (after 24 hours)	N/A
b) Dynamic Loading (1000 cycles)	11.4%
AS 4288 – 2003 Classification	Heavy Commercial
Foam	Re-bonded Polyurethane Treated with Ultra-Fresh™

## PACKAGING INFORMATION

	Length (m)	Width (m)	Area (m <sup>2</sup> )	Weight (kg)	Polywrap
Individual Rolls	10	1.80	18	15	Ultralay Light Blue Wrap Printed Black Polyethylene

Ultralay is a Registered trade name.

All statements and technical information contained herein are based on tests we believe to be reliable but the accuracy thereof is not guaranteed. Industry Purchasers assume all risk and liability resulting from the use of this product and must confirm the suitability thereof by their own test. Conditions of Sale contain a limited warranty against manufacturing defects.

Version No: 1.3	Effective Date: December 2008	Document No: DF8419
Location: DMS		Page 1 of 1
PRINTED COPY - UNCONTROLLED		